

Concrete curing agent

## PELICURA® PAR 156

### PRODUCT

**PELICURA® PAR156** is a curing agent based on paraffin emulsion to cure concrete, preventing rapid evaporation of water. It can be applied on external and internal floors.

**PELICURA® PAR156** meets the ASTM C309 standard.

### SEGMENTS OF USE

- Road pavement;
- Airport concrete runway;
- Industrial floors;
- Slabs;
- Channels, etc.

### APPLICATION

**PELICURA® PAR 156** must be applied with a spray on fresh concrete once the concreting process is finished and immediately after the exudation water disappears or when the concrete acquires a matte appearance.

On polished floors, apply after finishing, using a sprayer or paint roller.  
After application it will form a uniform film.

DO NOT DILUTE THE PRODUCT, READY TO USE.  
Shake the product on the packaging before applying.

**REMOVAL:** the removal of **PELICURA® PAR 156** must be done before receiving any type of coating, paint, mortar or chemical densifiers.

Film removal can be done using the *Remocon Super*.  
(consult technical department)

Outside, protect from rain for at least 3 hours.

### TOOL CLEANING

Clean with water or kerosene immediately after use.

### BENEFITS

- Reduces cracking;
- Improves cement hydration;
- Avoid losses of strength of the concrete;
- Reduces operational costs of wet curing.

### CHARACTERISTICS AND PERFORMANCE PHYSICAL PROPERTIES

CHARACTERISTICS	RESULTS
Use	Curing agent
Chemical basis	Paraffin emulsion
Appearance	White milky liquid
Density	0,98 Kg/L
PH	8,0 ± 1,0
Drying time	30 à 40 minutes (a 21°C)
Application temperature	from 0°C to 35°C
Package	Pail 19,6Kg, Barrel 49 Kg and 196 Kg

**PERFORMANCE:** 200mL/m<sup>2</sup>.

Consumption may vary depending on texture, porosity, wind and heat.

### CERTIFICATE

The **PELICURA® PAR 156** product complies with the ASTM C309 standard, according to ABCP certificate No. 129.258  
(Brazilian Portland Cement Association).

Technical information is based on laboratory tests.  
Actual application conditions and value measurements may vary due to conditions beyond our control.

### HYGIENE AND SAFETY

Users should wear protective goggles and rubber gloves. Direct contact with the skin should be avoided (may cause irritation). In case of contact with the skin or eyes, wash immediately with plenty of water and consult a doctor. Keep out of reach of children and animals.

### STORAGE

**PELICURA® PAR 156** must be stored in a dry and ventilated place at a temperature of 0°C to 35°C, in the original packaging.

### SHELF LIFE

8 months from the date of manufacture, in the original sealed packaging.